



## Standard Specification for Hot-Rolled and/or Cold-Finished Hafnium Rod and Wire<sup>1</sup>

This standard is issued under the fixed designation B 737; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers hot- or cold-worked hafnium rod and wire, or both.

1.2 This specification contains two material grades, one specifically for nuclear applications (Grade R1) and one for commercial applications for alloying (Grade R3).

1.3 The products covered include the following:

1.3.1 Rod  $\frac{3}{8}$  to 1.0 in. (9.5 to 25.4 mm) in diameter.

1.3.2 Wire less than  $\frac{3}{8}$  in. (9.5 mm) in diameter.

1.4 The values stated in inch-pound units are to be regarded as the standard. The SI units given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*

E 8 Test Methods for Tension Testing of Metallic Materials<sup>2</sup>

E 21 Test Methods for Elevated Temperature Tension Tests of Metallic Materials<sup>2</sup>

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications<sup>3</sup>

### 3. Terminology

3.1 *Lot Definitions:*

3.1.1 *castings*—a lot shall consist of all castings produced from the same pour.

3.1.2 *ingot*—no definition required.

3.1.3 *rounds, flats, tubes, and wrought powder metallurgical products (single definition, common to nuclear and non-nuclear standards)*—a lot shall consist of a material of the same size, shape, condition, and finish produced from the same ingot or powder blend by the same reduction schedule and the

same heat treatment parameters. Unless otherwise agreed between manufacturer and purchaser, a lot shall be limited to the product of an 8 h period for final continuous anneal, or to a single furnace load for final batch anneal.

3.1.4 *sponge*—a lot shall consist of a single blend produced at one time.

3.1.5 *weld fittings*—definition is to be mutually agreed upon between manufacturer and the purchaser.

### 4. Ordering Information

4.1 Purchase orders for material under this specification shall include the following information as required to adequately describe the desired material:

4.1.1 Quantity (weight or number of pieces),

4.1.2 Name of material,

4.1.3 Form (rod, wire),

4.1.4 Metallurgical condition (Section 6),

4.1.5 Finish (Section 12),

4.1.6 Applicable dimensions (diameter and length),

4.1.7 Grade (Table 1), and

4.1.8 ASTM designation and year of issue.

NOTE 1—A typical ordering description is as follows: 500 lb hafnium rod, annealed; mechanically descaled and pickled; 0.375 in. diameter by 6 in. minimum random lengths; Grade R1; ASTM Specification B 737.

4.2 In addition to the data specified in 4.1, the following options and points of agreement between the manufacturer and the purchaser shall be specified on the purchase order if required:

4.2.1 Mechanical test temperature (see 8.1),

4.2.2 Tolerances (Section 10),

4.2.3 Workmanship standards (Section 13),

4.2.4 Special tests (Section 11),

4.2.5 Inspection (Section 16),

4.2.6 Zirconium analysis requirements (Table 1), and

4.2.7 The isotopic hafnium composition and its analysis, if required, shall be mutually agreed upon by the purchaser and producer.

### 5. Materials and Manufacture

5.1 Material covered by this specification shall be made by conventional hot and cold working procedures, from ingots produced by vacuum melting in electron beam or consumable

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.02 on Zirconium and Hafnium.

Current edition approved Nov. 10, 2001. Published January 2002. Originally published as B 737 – 84. Last previous edition B 737 – 90 (2000).

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 03.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 14.02.

**TABLE 1 Chemical Requirements**

Composition, Weight %		
Element	Alloying Grade	
	Grade R1	Grade R3
Aluminum	0.010	0.050
Carbon	0.015	0.025
Chromium	0.010	0.050
Copper	0.010	...
Hydrogen	0.0025	0.0050
Iron	0.050	0.0750
Molybdenum	0.0020	...
Nickel	0.0050	...
Niobium	0.010	...
Nitrogen	0.010	0.0150
Oxygen	0.040	0.130
Silicon	0.010	0.050
Tantalum	0.020	...
Tin	0.0050	...
Titanium	0.010	0.050
Tungsten	0.0150	0.0150
Uranium	0.0010	...
Vanadium	0.0050	...
Zirconium	<sup>A</sup>	<sup>A</sup>
Hafnium	balance	balance

<sup>A</sup> Zirconium shall be reported. Acceptable levels shall be established by mutual agreement between purchaser and producer.

arc furnaces, or both, of a type conventionally used for reactive metals.

## 6. Metallurgical Condition

6.1 All grades furnished under this specification shall be in the recrystallization annealed condition unless otherwise specified.

## 7. Chemical Composition

7.1 The material shall conform to the requirements for chemical composition as prescribed in Table 1.

7.2 The manufacturer's ingot analysis shall be considered the chemical analysis for material produced to this specification except for hydrogen and nitrogen content which shall be determined on the finished product.

7.3 Analysis shall be made using the manufacturer's standard methods. In the event of disagreement as to the chemical composition of the metal, methods of chemical analysis for reference purposes shall be determined by a mutually acceptable laboratory.

7.4 Sampling for chemical composition shall consist of samples taken at top, middle, and bottom of the ingot. Samples for hydrogen and nitrogen shall be taken as two random samples from each lot at final size.

## 8. Mechanical Properties

8.1 Grade R1 in rod form shall conform to the requirements prescribed in Table 2 for room temperature mechanical properties. Elevated temperature properties shall be used to deter-

mine compliance only when specified in the purchase order (see Test Methods E 21).

8.2 The yield strength shall be determined by the offset (0.2 %) method as prescribed in Test Methods E 8.

8.3 The tensile properties shall be determined using a strain rate of 0.003 to 0.007 in./in.·min through the yield strength. After the yield strength has been exceeded, the cross-head speed shall be increased to approximately 0.05 in./in.·min to failure.

8.4 Requirements for mechanical properties do not apply to wire.

## 9. Corrosion Properties

9.1 Two samples chosen at random from each lot shall be corrosion tested in water at 680°F (360°C), 2690 psi (18.5 MPa) for 672 + 8 – 0 h using the manufacturer's standard procedure.

9.2 *Grade R1*—Coupons shall exhibit a weight gain of not more than 10 mg/dm<sup>2</sup>.

9.3 *Grade R3*—Test for information only, if required by purchase order.

## 10. Permissible Variations in Dimensions

10.1 Rod and wire shall conform to the dimensional requirements for the specified product as prescribed in Tables 3-5.

## 11. Special Tests

11.1 Additional tests may be specified in the purchase order. The test method and standards shall be agreed upon in advance between manufacturer and purchaser.

## 12. Finish

12.1 Rods shall be furnished with one of the following surface finishes as designated in the purchase order:

- 12.1.1 Mechanically descaled and pickled,
- 12.1.2 Centerless ground and pickled, or
- 12.1.3 Centerless ground, pickled, and oxidized.

12.2 Wire shall be furnished with one of the following surface finishes as designated in the purchase order:

- 12.2.1 Conditioned and pickled, or
- 12.2.2 Conditioned, pickled, and oxidized.

## 13. Workmanship

13.1 Cracks, seams, slivers, blisters, burrs, and other injurious imperfections shall not exceed standards of acceptability agreed upon by the manufacturer and the purchaser.

## 14. Number of Test and Retests

14.1 Two random samples shall be taken from each lot.

14.2 If any sample or specimen exhibits obvious contamination, improper preparation, or flaws disqualifying it as a representative sample, it shall be discarded and a new sample or specimen substituted.

**TABLE 2 Mechanical Properties**

Grade	Condition	Test Temperature	Tensile Strength, min ksi (MPa)	Yield Strength, min ksi (MPa)	Elongation in 2 in. or 50 mm, min, %
R1	annealed	RT	58 (400)	22 (151)	22
	annealed	600°F (316°C)	25 (172)	11 (83)	32

**TABLE 3 Permissible Variations in Diameter for Hot- or Cold-Finished Rod and Wire**

Diameters, in. (mm)	Permissible Variations, in. (mm) <sup>A</sup>	
	Over	Under
Up to 3/16 (4.8), incl	0.002 (0.05)	0.002 (0.05)
Over 3/16 to 5/8 (4.8 to 16.0), incl	0.003 (0.08)	0.003 (0.08)
Over 5/8 to 3/4 (16.0 to 19.0), incl	0.004 (0.10)	0.004 (0.10)
Over 3/4 to 1.0 (19.0 to 25.4), incl	0.005 (0.13)	0.005 (0.13)

<sup>A</sup> When it is necessary to heat treat or heat treat and pickle after cold finishing, because of special hardness, surface or mechanical property requirements, tolerances are double those shown in the table.

14.3 If the results of any test lot are not in conformance with the requirements of this specification, the lot may be retested at the option of the manufacturer. The frequency of the retest will be double the initial number of tests and if the results of the retest conform to the specification, then the retest values will become the test values for certification. All test values, original and retest, shall be reported to the purchaser.

### 15. Significance of Numerical Limits

15.1 For the purpose of determining compliance with the specified limits for requirements of the properties listed in the following table, an observed value or a calculated value shall be rounded as indicated in accordance with the rounding methods of Practice E 29.

Property	Rounded Unit for Observed or Calculated Value
Chemical composition, and tolerances (when expressed as decimals)	nearest unit in the last right-hand place of figures of the specified limit
Tensile strength and yield strength	nearest 1000 psi (10 MPa)
Elongation	nearest 1 %

### 16. Inspection

16.1 The manufacturer shall inspect the material covered by this specification prior to shipment. If so specified in the purchase order, the purchaser or his representative may witness the testing and inspection of the material at the place of manufacture. In such cases, the purchaser shall state in his purchase order which test he desires to witness. The manufacturer shall give notice to the purchaser as to the time and place of the designated tests. If the purchaser's representative does not present himself at the time agreed upon for the testing, the manufacturer shall consider the requirement for purchaser's inspection at place of manufacture to be waived.

16.2 The manufacturer shall afford the inspector representing the purchaser, without charge, all reasonable facilities to

satisfy him that the material is being furnished in accordance with this specification. This inspection shall be so conducted as not to interfere unnecessarily with the operation of the works.

### 17. Rejection

17.1 Rejection for failure of the material to meet the requirements of this specification shall be reported to the manufacturer within 60 calendar days from the receipt of the material by the purchaser. Unless otherwise specified, rejected material may be returned to the manufacturer at the manufacturer's expense, unless the purchaser receives, within 3 weeks of the notice of rejection, other instructions for disposition.

### 18. Referee

18.1 In the event of disagreement between the manufacturer and the purchaser on the conformance of the material to the requirements of this specification or any special test specified by the purchaser, a mutually acceptable referee shall perform the tests in question. The results of the referee's testing shall be used in determining conformance of the material to this specification.

### 19. Certification

19.1 When specified in the purchase order or contract, a producer's or supplier's certification shall be furnished to the purchaser that the material was manufactured, sampled, tested, and inspected in accordance with this specification and has been found to meet the requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

### 20. Packaging and Package Marking

20.1 Each shipment shall be legibly and conspicuously marked or tagged with the following information:

- 20.1.1 Purchase order or contract number,
- 20.1.2 Name of material,
- 20.1.3 Grade,
- 20.1.4 Size,
- 20.1.5 Lot, heat or ingot number,
- 20.1.6 Condition,
- 20.1.7 Gross, net, and tare weights, and
- 20.1.8 ASTM specification designation number.

20.2 All material shall be packaged in such a manner as to ensure safe delivery to its destination when properly transported by any common carrier.

### 21. Keywords

- 21.1 hafnium; hafnium alloy; rod; wire

**TABLE 4 Permissible Variations in Length for Hot- or Cold-Finished Rod and Wire**

Diameter, in. (mm)	Permissible Variations, in. (mm)		
	Under 3 ft (1m)	3–12 ft (1–4m)	Over 12 ft (4m)
Up to $\frac{3}{8}$ (9.5), incl	+ $\frac{1}{4}$ , - 0 ( + 6.4, - 0)	+ $\frac{1}{2}$ , - 0 ( + 13.0, - 0)	+ $\frac{3}{4}$ , - 0 ( + 19.0, - 0)
Over $\frac{3}{8}$ to 1.0 (9.5 to 25.4)	+ $\frac{1}{4}$ , - 0 ( + 6.4, - 0)	+ $\frac{3}{8}$ , - 0 ( + 9.5, - 0)	+ $\frac{1}{2}$ , - 0 ( + 13.0, - 0)

**TABLE 5 Permissible Variations in Straightness for Straight Lengths Hot- or Cold-Finished Rod and Wire<sup>A</sup>**

Diameter, in. (mm)	Permissible Variations
Up to $\frac{3}{8}$ (9.5), incl	$\frac{3}{32}$ in. (2.4 mm) in any 5 ft (1.5 m) but may not exceed $\frac{3}{32}$ in. (2.4 mm) $\times$ (number of feet in length/5)
Over $\frac{3}{8}$ to 1.0 (9.5 to 25.4)	$\frac{1}{16}$ in. (1.6 mm) in any 5 ft (1.5 m) but may not exceed $\frac{1}{16}$ in. (1.6 mm) $\times$ (number of feet in length/5)

<sup>A</sup>The measurement is taken on the concave side of the bar with a straight- edge. Unless otherwise specified, hot- or cold-finished bars for machining purposes are furnished machine straightened to the tolerances specified in the table.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).